



Ph 07 3423 5300  
www.georgeweston.com.au

## MATERIAL DATA SHEET

### LG2 BRONZE

**Commonly known as** LG2, 836, Leaded Gunmetal, BC6C, conforms to BS 1400- 1985 LG2 and AS1565 83600

#### Typical Applications

Suitable for bearings with light loads at low to medium speeds; light duty gears with negligible loading; pump and valve components. Reasonable corrosion resistance in seawater. Not subject to dezincification.

#### Chemical Composition %

Element		Nominal
Copper	Cu	balance
Tin	Sn	4.0 - 6.0
Lead	Pb	4.0 - 6.0
Zinc	Zn	4.0 - 6.0
Nickel	Ni	1.0 max
Iron	Fe	0.30 max
Aluminium	Al	0.01 max
Antimony	Sb	0.20 max

#### Mechanical Properties

Ultimate Tensile Strength	245 MPa minimum
Elongation	15% minimum
Typical Hardness	60 BHN
Machinability	84 % (free machining brass = 100%)

#### Similar Specifications

UNS C83600; BS1400-1985 LG2; ASTM 836; JIS H5111-BC6; DIN 1705-RG5; SAE 40

*The information contained in this website is provided by George Weston & Sons Pty Ltd and while we endeavour to keep the information up to date and correct, does not offer a guarantee of accuracy, completeness, reliability, suitability or availability. George Weston & Sons Pty Ltd is not liable for any consequences that result from the use of this information.*